

VRLA Rechargeable Battery

BPS10-12 (BPS10-12FR)

FEATURES

- Maintenance free(no water topping-up required)
- No free acid(Non-spillable battery)
- Can be used in any orientation(excluding used inverted)
- Absorbent Glass Mat technology for efficient gas recombination

APPLICATION

- UPS
- Laboratory
- Equipment



SPECIFICATIONS


Nominal Voltage	12V	
Nominal Capacity	20 Hour Rate (500mA, 10.5V)	10.0 Ah
	10 Hour Rate (950mA, 10.5V)	9.50 Ah
	5 Hour Rate (1700mA, 10.5V)	8.50 Ah
	1 Hour Rate (6000mA, 9.30V)	6.00 Ah
Approx. Weight	3300g(7.28lbs.)	
Terminals	T2 (Faston Tab 250) T1 is optional	
Max. Discharge Current	150 A (5 sec.)	
Max. Charge Current	3.00 A	
Operating Temperature Range	Charge	0°C~40°C(32°F~104°F)
	Discharge	-20°C~50°C(-4°F~122°F)
	Storage	-20°C~40°C(-4°F~104°F)
Self Discharge	< 3% per month (25°C)	
Internal Resistance	≤17mΩ (Fully Charged)	

CONTAINER MATERIAL


- BPS10-12:
ABS: UL 94-HB (Dark gray color)
- BPS10-12FR:
ABS: UL 94-V0 (Light gray color)

 ISO 9001	 ISO 14001
 MH19884 UL	 C4M20310-2474-E-16 CE
<ul style="list-style-type: none"> ● IEC61056 ● GB/T 19639 	<ul style="list-style-type: none"> ● JIS C 8702


OUTER DIMENSIONS mm(inch)	Length (L)	Width (W)	Container Height (H)	Total Height (TH)
		151±1.5(5.94±0.06)	65±1.5(2.56±0.06)	112±1.5(4.41±0.06)




TERMINAL TYPE



BPS10-12 (BPS10-12FR) discharge characteristics (25°C /77°F)




Battery Charging Characteristics



Charging Procedure

Application	Charging method	Charging Voltage at 25°C (V/cell)	Temperature compensation coefficient of charging voltage (mV/°C /cell)	Max. charging current (CA)	Charging time 0.1CA, 25°C (h)		Temp (°C)
					100% discharge	50% discharge	
For standby power Source	Constant voltage & Constant current charging (with current restriction)	2.25~2.30	-3	0.3	24	20	0~40 (32~104°F)
For cycle service		2.40~2.50	-4	0.3	16	10	

Effect Of Temperature On Long Term Float Life



Constant power discharge characteristics at 25 °C/77 °F Unit: W

F.V. (V/cell) \ Discharge Time	5 Min	10 Min	15 Min	30 Min	1 Hr	3 Hr	5 Hr	10 Hr	20 Hr
1.80V	361.6	266.2	213.3	126.9	72.78	29.15	20.10	11.23	5.91
1.75V	418.5	288.4	223.1	131.7	74.96	29.73	20.40	11.40	6.00
1.70V	444.6	298.7	230.0	134.7	76.31	30.00	20.51	11.46	6.04
1.65V	464.6	305.9	235.3	136.6	77.23	30.21	20.58	11.49	6.05
1.60V	480.0	312.0	240.0	138.0	78.00	30.39	20.64	11.49	6.05

Constant current discharge characteristics at 25 °C/77 °F Unit: A

F.V. (V/cell) \ Discharge Time	5 Min	10 Min	15 Min	30 Min	1 Hr	3 Hr	5 Hr	10 Hr	20 Hr
1.80V	32.57	23.43	18.55	10.75	6.12	2.43	1.675	0.936	0.493
1.75V	38.39	25.38	19.40	11.16	6.30	2.48	1.700	0.950	0.500
1.70V	40.79	26.30	20.00	11.42	6.41	2.50	1.709	0.955	0.503
1.65V	42.62	26.93	20.46	11.58	6.49	2.52	1.715	0.958	0.504
1.60V	44.04	27.46	20.87	11.69	6.55	2.53	1.720	0.958	0.504

All data shall be changed without prior notice, BB reserves the right to explain and update the information contained hereinto.

A/0 REV. Aug. 2009

USA:
B&B BATTERY(USA) INC.
6415 RANDOLPH ST.COMMERCE, CA,90040 U.S.A.
TEL:1-323-278-1900.1-800-278-8599
FAX:1-323-278-1268
E-Mail:sales@bb-battery.com

CHINA FACTORY:
B. B. BATTERY CO., LTD.
CHENG DONG TRIAL AREA,HUANG GANG,
RAOPING, GUANG DONG,CHINA,515700
TEL:86-768-7601001-2
FAX:86-768-7601469
E-Mail:maggy@bb-battery.com

EUROPE:
B&B BATTERY(EUROPE) B.V.
LAAN VAN KRONENBRUG 8, 1183AS
AMSTELVEEN, THE NETHERLANDS
TEL: +852-91282711
MOBILE: +852-91282711
E-Mail: dliu@bb-battery.com

HONG KONG:
NATIONAL TRADING LTD.
TEL:852-2301-3800
FAX:852-2739-1182
E-Mail:bbhk@hkstar.com

JAPAN:
B&B BATTERY(JAPAN) CO., LTD.
1375-11 NARAHARA-MACHI,HACHIOJI,
TOKYO 193-0803,JAPAN.
TEL:81-426-25-6375
FAX:81-426-25-6375
E-Mail:miyata@bb-battery.com

TAIWAN:
B. B. BATTERY(TAIWAN) CO., LTD.
TEL:886-6-502-5150
FAX:886-6-589-8087
E-Mail:maggy@bb-battery.com